





Sample Report

Further inquiries to: info@phasis.ch

Company: PHASIS Sàrl – Geneva, Switzerland

Comments: AFM on Au111 on mica, thickness 200nm



-- Area Roughness --

Area	100.8µm ²
Sa	835.91µm
Sq	1136.1µm
Sy	16.002nm
Sp	8.0009nm
Sv	-8.0009nm
Sm	135.01µm

-- Area Roughness --

Area	100.8µm ²
Sa	995.28µm
Sq	1307.9µm
Sy	13.018nm
Sp	6.3736nm
Sv	-6.6448nm
Sm	130.25µm