

## Glass properties

### Borosilicate

Refractive index ( $\lambda=589.3\text{nm}$ )	1.507
Annealing point	722°C
Thermal coefficient of expansion (0 – 300°C)	$31.8 \cdot 10^{-7} \text{ }^\circ\text{C}^{-1}$
Density	2.37 g/cm <sup>3</sup>
Dielectric constant	5.18 @20°C, 1kHz

Please contact us for detailed information.