

Glass properties  
SF10

Refractive index ( $\lambda=589.3$ nm)	1.728
Transformation temperature	454°C
Thermal coefficient of expansion (20 – 300°C)	$8.4 \cdot 10^{-6} \text{ K}^{-1}$
Density	4.28 g/cm <sup>3</sup>

Please contact us for detailed information.