

Glass properties

Quartz

Refractive index ($\lambda=589.3$ nm)	1.4585
Annealing point	1213.8°C
Thermal coefficient of expansion (20 – 320°C)	$5.5 \cdot 10^{-7} \text{ }^\circ\text{C}^{-1}$
Density	2.21 g/cm ³
Dielectric constant	3.7 @20°C, 1MHz

Please contact us for detailed information.