

Glass properties  
Borosilicate

Refractive index ( $\lambda=589.3$ nm)	1.523
Annealing point	557°C
Thermal coefficient of expansion (20 – 300°C)	$7.2 \cdot 10^{-6} \text{ K}^{-1}$
Density	$2.51 \text{ g/cm}^3$
Dielectric constant	6.7 @20°C, 1MHz

Please contact us for detailed information.